

# Test Report

Report No.: A001R20161227108-2

Date: Jan.07, 2017

Page 1 of 3

Applicant: HUIZHOU TOP PACKAGING PRODUCTS CO., LTD  
Address: Floor 2,Building 5, Jun Yuan Industrial Park,Bai Shi Village,Qiu Chang Town,Hui Yang  
District,Hui Zhou.

## Report on the submitted sample(s) said to be:

Sample Name : Window Kraft paper bag  
Material : MOPP/kraft/PET/copolymerization CPP  
Sample Received Date : Dec.27, 2016  
Testing Period : Dec.27, 2016 to Jan.07, 2017  
Test Requested : Please refer to next page(s).  
Test Method : Please refer to next page(s).  
Test Result : Please refer to next page(s).

Tested by:

*Eva Lin*

LinYE, Eva.Lin

Test Engineer

Reviewed by:

*Henry*

Zhaoliang, Henry

Laboratory Supervisor

Approved by:

*Lewis*

Liulinwen, Lewis

Technical Director



The results shown in this test report refer only to the sample(s) tested unless otherwise stated and the sample(s) are retained for 30 days only. The document is issued by AGC, this document cannot be reproduced except in full with our prior written permission. The more details and the authenticity of the report will be confirmed at <http://www.agc-cert.com>.

Attestation of Global Compliance

**No.16 C**

Tel: +86-755 8358 3833 Fax: +86-755 2531 6612 E-mail: [agc01@agc-cert.com](mailto:agc01@agc-cert.com) 400 089 2118  
Add: Building 2, No.171, Meihua Road, Shangmeilin, Futian District, Shenzhen, Guangdong China

# Test Report

**Report No.: A001R20161227108-2**
**Date:** Jan.07, 2017

**Page 2 of 3**
**Test Requested:**

As specified by client, to test sample with reference to the US Food And Drug Administration (FDA) the food contact test standard: 21 CFR 177.1520.

- N-hexane extractives
- Xylene extractives
- Density

**Conclusion**

**Pass**  
**Pass**  
**Pass**

**Test Result(s):**
**Test result of FDA 21 CFR 177.1520**

| Test Item            | Test condition | Unit              | MDL | Result(s)   | Limit     |
|----------------------|----------------|-------------------|-----|-------------|-----------|
|                      |                |                   |     | 1           |           |
| N-hexane extractives | 50°C, 2h       | %                 | 0.2 | 0.5         | 5.5       |
| Xylene extractives   | Reflux, 2h     | %                 | 0.2 | 3.2         | 30        |
| Density              | /              | g/cm <sup>3</sup> | -   | 0.89        | 0.85~1.00 |
| <b>Conclusion</b>    | /              | /                 | /   | <b>Pass</b> | /         |

**Note:**

1. N.D.=not detected (less than method detection limit)
2. MDL= method detection limit

**Sample Description**

|   |  |
|---|--|
| 1 | Inner transparent plastic bag (copolymerization CPP) |
|---|--|

The results shown in this test report refer only to the sample(s) tested unless otherwise stated and the sample(s) are retained for 30 days only. The document is issued by AGC, this document cannot be reproduced except in full with our prior written permission. The more details and the authenticity of the report will be confirmed at <http://www.agc-cert.com>.



## Test Report

Report No.: A001R20161227108-2

Date: Jan.07, 2017

Page 3 of 3

### The photo of the sample



AGC authenticate the photo on original report only

\*\*\* End of Report \*\*\*

The results shown in this test report refer only to the sample(s) tested unless otherwise stated and the sample(s) are retained for 30 days only. The document is issued by AGC, this document cannot be reproduced except in full with our prior written permission. The more details and the authenticity of the report will be confirmed at <http://www.agc-cert.com>.

**Attestation of Global Compliance**

**No.16 C**

Tel: +86-755 8358 3833 Fax: +86-755 2531 6612 E-mail: [agc01@agc-cert.com](mailto:agc01@agc-cert.com) 400 089 2118  
Add: Building 2, No.171, Meihua Road, Shangmeilin, Futian District, Shenzhen, Guangdong China